

Technical Data Sheet

Anti Corrosion Primer

Roofing

7 Day Technical Support 1800 655 711

Testing Approvals: N/A

Description

Anti Corrosion Primer is a water-based acrylic, anticorrosive etch primer, formulated with flash rust inhibitors and zinc phosphate to provide long term corrosion protection on metal surfaces.

Features and Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Highly efficient Corrosion Inhibitor/Pacifier • Exceptional adhesion • Very low water permeability • Tough film • Rapid drying • Non-flammable | <ul style="list-style-type: none"> • Ease of application • May be coated with many types of paint (test for suitability before use) • Suitable to be over coated with Crommelin® Membryl and Crommelin® Fibroseal®. |
|---|--|

Areas of Use

- | | |
|--|--|
| <ul style="list-style-type: none"> • Iron • Galvanized Iron • Zincalume | <ul style="list-style-type: none"> • Steel • Aluminium • Light to Medium Corroded substrate |
|--|--|

Technical Data

Number of Coats:		Recoat (@25°C):	2 hours
Light Corrosion	1	Curing time:	4 hours
Medium Corrosion	2	Colour:	Light Grey
Spreading Rate Per Coat:	7-12m ² /L	Thinner:	Water
Wet Film Per Coat:	45-140 microns	Shelf Life:	12 months

Application Guide

Surface Preparation

- Surfaces must be clean, dry, free of dust and in a sound condition.
- New galvanized iron and zincalume surfaces should be degreased by thoroughly scrubbing with a nylon scourer and a hot water detergent solution. Rinse well with clean water.
- For unpainted galvanized iron and zincalume, with light to medium corrosion to surfaces, high pressure water blast and allow dry prior to applying **Anti Corrosion Primer**.
- For previously painted galvanized iron and zincalume, with light to medium corrosion to surfaces, the area must be wire brushed to remove all loose material, then high pressure water blasted and allowed to dry prior, to applying **Anti Corrosion Primer**.

Technical Data Sheet

Anti Corrosion Primer

Roofing

7 Day Technical Support 1800 655 711

Application Guide (continued)

Application Procedure and Equipment

- Stir well before use using a broad flat paddle.
- Apply by brush, roller or spray evenly.
- **Anti Corrosion Primer** is best applied by convention or airless spray. Small areas may be applied by brush or roller. The product is best applied neat, however 5-10% water may be added to aid application.

Precautions

- Do not apply if temperature is below 10°C or relative humidity is above 85% or rain is imminent.

Cleaning

- Wash equipment in water before **Anti Corrosion Primer** dries.

Health and Safety

Safety Precautions

- Provide good ventilation – open windows and doors and use circulating fans.
- If product is splashed on skin it should be washed off with water before it can dry.
- Wear gloves and eye protection during application.

First Aid

Swallowed: Contact a doctor or Poisons Information Centre. Do not induce vomiting. Give water to drink.

Eye: Gently flush with running water, holding eyelids open for 15 mins. Seek medical attention.

For detailed information refer to product label and the current Material Safety Data Sheet available from Crommelin®. In the case of an emergency please call the Poisons Information Centre on 13 11 26

Transport and Storage

Sizes:	20L	Flash Point:	N/A
Weights:	26Kg	UN Number:	N/A
Dangerous Goods Class:	N/A		

Disclaimer

Crommelin® and other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks. Any advice, recommendation, information, assistance or service provided by Crommelin® in relation to its products or their use is given in good faith, however is provided without responsibility or liability. Customers need to undertake their own assessment to determine the suitability of a product for the particular use intended. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs on the specific surface.