



Sikkens

Cetol® Deck Slip Resistant

Description

Durable premium, oil-based, translucent, fine-textured, anti-slip timber stain for decks, steps and walkways. Based on a special oil-alkyd resin combination and selected UV-absorbing pigments for optimum protection and aesthetics.

Main properties / U.S.P.s

GENERAL

- High transparency ensures optimum visibility of the timber grain
- Withstands physical wear
- Micro porous: allows timber to breath
- Weather resistant
- Water repellent
- Easy application and maintenance
- Slip Resistant Classification of R11 and P4

Use

Decks, Steps, and Handrails: as a finish coating (2 coats) on a correctly prepared and primed timber. On bare timber, a priming coat of Cetol® HLSe is highly recommended to improve adhesion and durability of Cetol® Deck Slip Resistant finish.

Sheen Density Package viscosity Solids content

PROPERTIES

Satin finish
Approx. 0.90 – 0.92 kg/dm³.
Approx. 45 - 50 sec ISO Cup 4 / 23°C.
By weight: approx. 42 - 44% - by volume: approx. 34 - 36%.

Outdoor durability

Coating lifespan on decks is short! Horizontal surfaces are completely exposed to the sun's ultraviolet rays. These areas also receive high levels of moisture which can sit on the surface for days or even weeks. Decks that are too low to the ground, have poor drainage or are not well ventilated beneath, do not allow moisture to escape from below the deck. This means that the timber is constantly subjected to moisture. Decks are also subject to physical damage from foot traffic (human and animal) and scraping from garden furniture. Physical damage to the coating accelerates deterioration caused by the elements to the timber beneath the coating's surface.

Generally, maintenance of timber decks should take place every year. An additional maintenance coat should be applied as and when the finish shows signs of wear. However, rapid deterioration of deck finishes can occur where there is constant water contact (e.g. nonstop spray from sprinkler systems), and on unventilated skirted decks. In such situations, Cetol® Deck Slip Resistant is not appropriate for use.

VOC (Volatile Organic Compound) Colour

EU limit value for this product (cat. A/e): max. 400 g/l (2010). This product contains max. 385 g/l VOC.

Cetol® Deck Slip Resistant comes in a 078-Natural (honey) colour.

FURTHER SUPPORT

If you need further support, please contact Crommelin on 1800 655 711 – 7 days. Crommelin is an authorised distributor of Sikkens Cetol Timber Finishes in Australia. Always read full Health, Safety & Environmental Information on can before use.

SYSTEM SPECIFICATION

Timber moisture content

Moisture content of timber to be coated should not exceed 18%. Excessive moisture content may prevent adhesion and penetration and hence can lead to blistering, flaking and blotchy finish.

Timber quality

Structural timber elements should be manufactured to the highest national quality standards for design and construction of joinery and house-front in-fillings.

Application New timber

New or unseasoned hardwood such as Merbau (Kwila), Spotted Gum, Tallowood, Jarrah and Ironbark contain natural tannins. These tannins need to be extracted prior to coating. This will happen naturally over a period of 3-6 months depending on exposure, or the process can be accelerated using Sikkens Cetol® Tannin & Oil Remover followed by Sikkens Cetol® Deck & Wood Cleaner.

1) Sand dense hardwood using 60-80 grit sandpaper, for softwood sand using 100-120 grit sandpaper.

2) For tannin-rich timbers, apply Sikkens Cetol® Tannin & Oil Remover according to on-pack instructions, allow to sit on the timber surface for 15 minutes before thoroughly rinsing with a pressure washer or hose. Whilst timber remains wet, apply a liberal coat of Sikkens Cetol® BL Deck & Wood Cleaner and scrub into the surface: leave for 15 minutes then rinse thoroughly with pressure washer or hose.

For timbers with no tannin content, wet the timber and apply Sikkens Cetol® BL Deck & Wood Cleaner or a similar solution for surface cleaning and rinse thoroughly.

Allow to dry completely prior to applying any coating.

3) Apply a priming coat of Cetol® HLSe in the selected colour. End grains, nail holes, cavities and cracks in the timber must be heavily coated.

4) Where necessary, fill holes with the right colour timber filler such as Sikkens Cetol® Gupa or Nordsjo Professional Flexible Wood Filler and allow to dry. Sand and dust and apply 2 finishing coats of Cetol® Deck Slip Resistant.

For best results, it is necessary to keep the interval between the priming and finishing coats as short as possible. This period should not exceed 1 month.

Recoating previously coated decks and timber

Revitalising timber with an intact finish

1) Clean using a stiff bristle brush, water and a mild detergent. Allow timber to dry thoroughly.

2) Lightly sand the deck with 120-150 grit sandpaper and dust down ensuring a clean surface. (Note: This may reduce slip resistant properties)

Flaking, peeling, weathered timber

1) Sand back to bare timber, remove any old product or residue.

2) Wet the timber and apply Sikkens Cetol® BL Deck & Wood Cleaner to clean the timber in just 20 minutes. Allow to dry completely prior to applying any coating.

FURTHER SUPPORT

If you need further support, please contact Crommelin on 1800 655 711 – 7 days.
Crommelin is an authorised distributor of Sikkens Cetol Timber Finishes in Australia.
Always read full Health, Safety & Environmental Information on can before use.



Sikkens
Cetol® Deck
Slip Resistant

	<p>To finish, follow steps 3 and 4 as above. Allow the coating to cure for 48 hours before subjecting to light foot traffic and 7-10 days for full cure (harden) and placing furniture (avoid dragging).</p>
Maintenance	<p>Inspect the finish on the surface at regular intervals (every 12 months or earlier). Depending on the condition of the finish, thoroughly clean, wash the deck with mild detergent and rinse well. If necessary, sand lightly using 180 grit paper. Ensure thorough drying prior to re-coating.</p> <p>When excessive dirt or staining of deck is present, wet the timber and apply Sikkens Cetol® BL Deck & Wood Cleaner or a similar solution and rinse thoroughly. Allow to dry completely.</p> <p>Repair any defects with Cetol® Gupa or Nordsjo Professional Wood Filler in the right colour. Allow to dry, sand and dust. Repair any color defects with Cetol® HLSe. Allow to dry and apply one or two further coat(s) of Cetol® Deck Slip Resistant overall.</p>
Application conditions	<p>APPLICATION INFORMATION</p> <p>Temperature between 10 – 35°C. Relative humidity max. 85%. Do not use when heavy rain or heavy dew is expected. Avoid applying in direct sunlight or under wet conditions.</p>
Application methods	<p>Ready for use after thorough stirring. Apply liberally in the direction of the grain using a good quality brush for optimum penetration. DO NOT use rollers or applicators.</p>
Thinning	<p>None. Ready for use after thorough stirring (thinning will reduce UV protection).</p>
Cleaning of equipment	<p>Clean brushes and equipment immediately after use with mineral turpentine/white spirit.</p>
Drying At 20°C/65% RH	<p>Tack free: after approx. 3 – 4 hours. Re-coatable: after approx. 24 hours.</p>
Coverage	<p>7.5 - 10 m²/l per coat and 3 coats. The coverage mainly depends on the wood species under treatment, the surface condition, the method of application and conditions during application.</p>
Packaging size	<p>100ml Sample pot, 1L, 5L and 20L.</p>
Shelf life Storage conditions	<p>Minimum 36 months in original and unopened packaging. Keep in a dry and cool place.</p> <p>Health and safety information: Flash point: Closed cup: 57°C Hazard statement: Warning: H226 - Flammable liquid and vapour. H373 - May cause damage to organs through prolonged or repeated exposure. H412 - Harmful to aquatic life with long lasting effects. Please refer to the Safety Data Sheet before use.</p>

FURTHER SUPPORT

If you need further support, please contact Crommelin on 1800 655 711 – 7 days.
Crommelin is an authorised distributor of Sikkens Cetol Timber Finishes in Australia.
Always read full Health, Safety & Environmental Information on can before use.

The Sikkens logo consists of a solid black horizontal bar above the word "sikkens" in a bold, lowercase, sans-serif font.

**Cetol® Deck
Slip Resistant**

The effectiveness of our product and systems is based on years of practical experience and research in our laboratories. We guarantee that the quality of the work on which our products are used meets the qualifications (AkzoNobel Decorative Paints) has promised, provided that all instructions given by us are correctly followed and the work has been carried out according to good craftsmanship. In case the end result has been influenced negatively by circumstances beyond our control, any and all liability are expressly excluded and disclaimed. Purchaser needs to check whether the delivered products are fit for the intended use. As soon as a new version of this (technical data sheet) is available, this one will no longer be valid.

FURTHER SUPPORT

If you need further support, please contact Crommelin on 1800 655 711 – 7 days.
Crommelin is an authorised distributor of Sikkens Cetol Timber Finishes in Australia.
Always read full Health, Safety & Environmental Information on can before use.