

Technical Data Sheet

Enhance Satin

Sealing

7 Day Technical Support 1800 655 711

Testing Approvals: N/A

Description	
<p>Enhance Satin is a tough satin finish surface treatment that provides protection, restores & enhances natural colours. The product has been modified to promote extremely low dirt pick up, making treated areas easier to maintain and keep clean. Worn or damaged areas can be recoated without stripping or grinding and most stains are easily removed by detergents.</p>	
Features and Benefits	
<ul style="list-style-type: none"> • Extends the life of concrete pavers by up to 40% • Provides a clear, non-yellowing film • Resists oils, grease and general dirt pick up 	<ul style="list-style-type: none"> • Suppresses efflorescence • Retains the natural colour of the pavers, even in heavy use areas
Areas of Use	
<ul style="list-style-type: none"> • All previously uncoated areas of concrete requiring a stain-resistant durable finish • Domestic walkways and driveways • Warehouse floors • Bus stations 	<ul style="list-style-type: none"> • Shopping malls • Pedestrian areas • Pattern concrete • Stencilled concrete
Technical Data	
Number of Coats: 2 Spreading Rate Per Coat: 1 st Coat (thinned 10%) 6m ² /L 2 nd Coat 5m ² /L Wet Film Per Coat: 167-200 microns	Recoat (@25°C): Min. 2 hours Curing time: 7 days Colour: Clear Thinner: Cleaning & Thinning Solvent Shelf Life: 12 months
Application Guide	
<p>Surface Preparation</p> <ul style="list-style-type: none"> • On newly paved areas remove all loose material with a dry, stiff bristle broom. • On weathered and worn paved areas remove all dirt, oil, grease and loose material using detergent and water, degreasers. Where necessary, moss and algae should be treated and removed, followed by high pressure water cleaning. • All surfaces must be thoroughly dry. Dampness in the pavers may spoil the clear finish, turning it milky. To test for moisture, tape a clear plastic sheet (300mm x 300mm) over the pavers in the most likely damp area. If moisture appears on the underside of the plastic within 2 hours, the pavers are too damp. Repeat inspection every couple of days until no moisture is present. <p>Application Procedure and Equipment</p> <ul style="list-style-type: none"> • Sealing of sloping surfaces may increase the potential for pedestrians to slip. Crommelin® Slip Resistive Additive (SRA) can be added to provide an improved slip resistant profile. Please ensure to follow the 'Application Procedure and Equipment' method, stated in Crommelin® Slip Resistive Additive (SRA) technical data sheet. • For airless spray, apply direct from the container at a pressure of 800 -1000 p.s.i. Thin as necessary with Crommelin® Cleaning & Thinning Solvent. 	

Technical Data Sheet

Enhance Satin

Sealing

7 Day Technical Support 1800 655 711

Precautions

- Do not apply if humidity is above 85% or if rain is imminent.
- Do not apply if temperature is over 35°C or under 5°C. Where hot windy conditions occur, apply in the morning.
- Enhance Satin may increase the slipperiness depending on the surface and the quantities of sealer used.

Cleaning and Maintenance

- Equipment can be cleaned with lacquer thinners or **Crommelin® Solvent**
- Any spills must be cleaned immediately. Spot cleaning should be carried out with diluted detergents or bleaches.
- It is recommended that areas treated be scrubbed or mechanically cleaned monthly using appropriate cleaning fluids.

Health and Safety

Safety Precautions

- Avoid breathing vapour. Wear organic vapour respirator meeting the requirements of AS1715 and AS1716.
- Provide good ventilation – open windows and doors and use circulating fans.
- Wear eye protection.
- Wear PVC or neoprene gloves. Avoid contact with skin.
- If product is splashed on skin it should be washed off with water before it can dry.
- Keep out of the reach of children.

First Aid

- Swallowed: If poisoning occurs contact a doctor or Poisons Information Centre. Do not induce vomiting. Risk of aspiration into lungs. Give water to drink.
- Eye: Gently flush with running water, holding eyelids open for 15 minutes. Seek medical attention.
- Skin: Remove contaminated clothing and gently flush affected areas with soap and water. Seek medical attention if irritation develops. Launder clothing before re-use.
- Inhalation: Remove patient from exposure, into fresh air. Apply artificial respiration if patient has stopped breathing. Seek medical attention.

For detailed information refer to product label and the current Material Safety Data Sheet available from Crommelin®.

In the case of an emergency please call the Poisons Information Centre on 13 11 26

Transport and Storage

Sizes:	15L, 200L	Flash Point:	43°C
Weights:	15Kg, 207Kg	UN Number:	1263
Dangerous Goods Class:	3.2	Poisons Schedule:	5
Hazchem Code:	3 (Y)		

Technical Data Sheet

Enhance Satin

Sealing

7 Day Technical Support 1800 655 711

Disclaimer

Crommelin® and other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks. Any advice, recommendation, information, assistance or service provided by Crommelin® in relation to its products or their use is given in good faith, however is provided without responsibility or liability. Customers need to undertake their own assessment to determine the suitability of a product for the particular use intended. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs on the specific surface.