



Elastoseal[®] PUV

Trafficable UV stable polyurethane membrane.

DESCRIPTION

Elastoseal[®] PUV is a high performance, low VOC, moisture-curing single-pack, elastomeric polyurethane waterproofing membrane.

Elastoseal[®] PUV is directly foot-trafficable and engineered for use in exposed conditions.

Note: It is not recommended to adhere tiles directly to Elastoseal[®] PUV.

ADVANTAGES

Elastoseal[®] PUV delivers the following advantages;

- Monolithic membrane – no lap, weld or seams.
- Low VOC, complies with Green Star requirements.
- High UV resistance.
- Quick tack-free surface.
- High resistance to puncture.
- High resistance to stagnant water.
- High resistance to fouling.
- High elongation, class III membrane.
- No reinforcement required.
- Excellent crack bridging capability.
- Remains flexible at low temperatures.

AREAS OF USE

Elastoseal[®] PUV is suitable for use in the following areas;

- Gutters & Roofs
- Roof Gardens & Terraces
- Wet Areas
- Podium Decks & Balconies

SUBSTRATES

Elastoseal[®] PUV is suitable for application on;

- Concrete & Brick
- Cement Render
- Cement Sheeting
- Aluminium & Steel
- Plywood Sheeting
- Light Weight Aggregate Block

TESTING APPROVALS AND STANDARDS

Elastoseal[®] PUV is compliant with the following standards;

- Green Star - Design & As Built v1.1: Indoor Pollutants 13.1 Paints, Adhesives, Sealants and Carpets.
- APAS 181 – V.O.C limits.
- AS4654 Waterproofing of External Above Ground Building Elements.

TECHNICAL DATA (@ 25°C)

Number of Coats:	2
Coverage: (per coat)	800gm/m ²
Wet Film: (per coat)	620 microns
Recoat:	12 – 48 hours maximum
Full Cure:	7 days
Colour:	Light Grey
Thinner/Clean Up:	Xylene
Shelf Life:	9 months

Elastoseal[®] PUV

Trafficable UV stable polyurethane membrane.

ANCILLARY PRODUCTS

- Crommelin[®] Contractor Polyurethane Sealant – 600ml
- Crommelin[®] Silicone WP Plus – 300ml
- Crommelin[®] Polyfab – reinforcing fabric
- Crommelin[®] Polyfab BB – bond breaker
- Crommelin[®] Contractor Membrane Applicator Brush – 100mm, 75mm
- Crommelin[®] Contractor Membrane Roller Cover – 230mm
- Crommelin[®] Moisture Meter

TEST DATA

Properties	Measurement /Standard	Test Results
Tensile Strength	AS1145	6MPa
Elongation	AS1145	300%
Hardness (Shore A)	In-house test method	70
Angle Tear Strength	In-house test method	20kg/cm
UV Resistance	In-house test method	Excellent

SUBSTRATE PREPARATION AND PRIMING

Full substrate preparation instructions can be found at www.crommelin.com.au/full-instructions/

- The surface should have a light even texture. Masonry should be flush pointed and all defects in existing surfaces made good.
- Surfaces must be clean, dry, sound and free from dust, grease, curing compounds, release agents, loose particles, efflorescence, concrete laitance or any other contaminants.
- All high points and protrusions should be removed, blow-holes and areas of honeycombing should be filled and the surface should be brought back to an even profile using a suitable repair mortar.

Note: Due to the wide variety of substrates available, adhesion testing is recommended in a trial area before full application.

- For maximum membrane adhesion, priming with Crommelin[®] Primer PU is recommended.
- If substrate is not dry, prime surface with Crommelin[®] WB2K as per specification.

APPLICATION CONDITIONS

- Substrate must be dry, with less than 15% moisture content. The use of suitable moisture meter is recommended.
- Application temperature between 10°C - 35°C.
- Do not apply if relative humidity is above 85% during initial cure phases, or if rain is expected before cure.

Note: In humid conditions, air flow should be maximised with the use of fans to assist cure.



7 Day Technical Support 1800 655 711

72 Division Street, Welshpool Western Australia 6106 T +61 8 9458 5711 F +61 8 9451 4749
service@crommelin.com.au www.crommelin.com.au

Elastoseal[®] PUV

Trafficable UV stable polyurethane membrane.

APPLICATION

Full application instructions can be found at www.crommelin.com.au/full-instructions/

- Apply Crommelin[®] Polyfab BB or Bond Breaking Sealant to internal angles/corners (wall & floor junction) and vertical angles/corners (wall & wall junction) as per standard.
- Apply Elastoseal[®] PUV with Crommelin[®] Contractor Membrane Brush, Crommelin[®] Contractor Membrane Roller or similar.
- Apply first coat of Elastoseal[®] PUV as per recommended coverage rate. Work from corners to central areas and allow to dry.
- If only a bond breaking sealant has been used, it is recommended to install Crommelin[®] PolyFab Reinforcing Fabric to all joints and corners in conjunction with first coat of Elastoseal[®] PUV.
- Apply second coat of Elastoseal[®] PUV (within 48 hours of the first coat) as per recommended coverage rate, at 90^o to the first coat.
- Allow to cure for a minimum of 24 hours, before the application of a screed or the commencement of tiling.
- If pond testing is required, allow to dry for a minimum 48 hours (depending on weather conditions) to ensure adequate curing. Pond test with water to a depth of 25mm for 2 hours. After testing ensure area is drained and dried.
- Elastoseal[®] PUV can be directly foot trafficable due to its high resistance to puncture and hardness. Vehicle traffic is not permitted on Elastoseal[®] PUV without the application of Crommelin[®] PUV Shield.

CLEAN UP

- Wash all equipment with Crommelin[®] Solvent, Xylene or MEK before product dries.

MAINTENANCE SCHEDULE AND REPAIR

- Elastoseal[®] PUV must be protected from damage by trades and inspected prior to the application of any over coat.
- Moisture blisters and bubbles may be repaired by cutting out the affected area, allowing substrate to properly dry and reapplication of membrane as per recommended coverage rates.
- Protect membrane from harsh chemicals, abrasion and other potentially damaging conditions.

PRECAUTIONS

- Do not apply if the temperature is below 10°C or relative humidity is above 85% or if rain is imminent.
- Do not apply Elastoseal[®] PUV to wet substrates. The moisture content of the surface should be less than 15%. Check with a moisture meter if unsure.
- Ensure adequate ventilation and air flow to optimise membrane curing.

WARRANTIES

A standard warranty period of 10 years is offered for Crommelin[®] Elastoseal[®] PUV.

Extended warranties are available for project specific applications. Please contact your Crommelin[®] representative, or the Crommelin[®] technical support team for detailed specifications applicable to your project and warranty requirements.

TRANSPORT AND STORAGE

- Size: 19kg
- Weight: 19kg
- DG Class: N/A
- Flash Point: N/A
- UN Number: N/A
- Cool and Dry Storage



7 Day Technical Support 1800 655 711

72 Division Street, Welshpool Western Australia 6106 T +61 8 9458 5711 F +61 8 9451 4749
service@crommelin.com.au www.crommelin.com.au

Elastoseal[®] PUV

Trafficable UV stable polyurethane membrane.

SAFETY AND FIRST AID

Elastoseal[®] PUV Safety Data Sheet is available from Crommelin[®] upon request.

Safety

- Ensure good ventilation and avoid breathing vapours.
- Avoid skin and eye contact. Wear gloves and eye protection. Remove splashes on skin immediately and remove contaminated clothing.
- Keep out of reach of children.
- Keep container sealed when not in use.
- Do not swallow.

First Aid

- If poisoning occurs, contact a doctor or poisons information centre: Ph. 13 11 26.
- If swallowed, do not induce vomiting. Give a glass of water to drink.
- If in eyes, hold eyes open and flood with water for at least 15 minutes.
- If not breathing, apply artificial respiration.

Crommelin[®] and other marks followed by ® are registered trademarks.

Any advice, recommendation, information, assistance or service provided by Crommelin[®] in relation to its products or their use is given in good faith, however is provided without responsibility or liability.

Customers need to undertake their own assessment to determine the suitability of a product for the intended use. As the performance of any product is subject to a wide variety of different surface types as well as environmental and surface-specific conditions, it is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs as required on the specific surface.

Crommelin[®] also reserves the right to update information without prior notice, to reflect ongoing research and product development.



7 Day Technical Support 1800 655 711

72 Division Street, Welshpool Western Australia 6106 T +61 8 9458 5711 F +61 8 9451 4749
service@crommelin.com.au www.crommelin.com.au