

CROMSHIELD™

Enhance Colours

Testing Approvals: N/A

Description

CROMSHIELD™ Enhance Colours is a 2L tinting system designed to compliment CROMSHIELD™ Enhance Satin and Gloss by providing a colour alternative to rejuvenating aged concrete and masonry. When used in conjunction with CROMSHIELD™ Enhance Satin or Gloss, CROMSHIELD™ Enhance Colours is an ideal alternative to paving paints.

Features and Benefits

- | | |
|---|---|
| <ul style="list-style-type: none"> • 2L tint to 15L CROMSHIELD™ Enhance Satin/Gloss • Available in 4 colours • Resists oils, grease and general dirt pick up | <ul style="list-style-type: none"> • 1 coat system provides a wash of colour • 2 coat system is needed to achieve opacity • Colour penetrates up 2mm |
|---|---|

Areas of Use

- | | |
|--|--|
| <ul style="list-style-type: none"> • All previously uncoated areas of concrete requiring a stain-resistant durable coloured finish • Domestic walkways and driveways • Warehouse floors | <ul style="list-style-type: none"> • Shopping malls & Bus stations • Pedestrian areas • Pattern concrete • Stencilled concrete |
|--|--|

Technical Data

Number of Coats:	2 (for solid colour)	Curing time:	7 days
Spreading Rate Per Coat:		Colour:	Limestone, Grey, Charcoal, Burnt Clay
1 st Coat (thinned 10%)	8m ² /L	Thinner:	Cleaning & Thinning Solvent
2 nd Coat	8m ² /L	Shelf Life:	12 months
Wet Film Per Coat:	167-200 microns		
Recoat (@25°C):	Min. 4 hours		

Application Guide

Surface Preparation

- Refer to CROMSHIELD™ Enhance Satin/Gloss Technical Data Sheets

Application Procedure and Equipment

- 2L of CROMSHIELD™ Enhance Satin/Gloss needs to be removed from the 15L container.
- The CROMSHIELD™ Enhance Colours needs to be added to the remaining 13L.
- This should be stirred thoroughly for 10 mins ensuring no air is entrained.
- Sealing of sloping surfaces may increase the potential for pedestrians to slip. Broadcasting CROMFLOOR™ Slip Resistive Additive over the first coat of sealer when it is still tacky will reduce the potential to slip. Before applying the 2nd coat, broom off any loose Slip Resistive Additive.
- For airless spray, apply direct from the container at a pressure of 800 -1000 p.s.i.
- Do not apply if temperature is over 35°C or under 5°C. Where hot windy conditions occur, apply in the morning.
- Thin as necessary using CROMSHEILD™ Solvent.

Precautions

- Do not apply if humidity is above 85% or if rain is imminent.
- CROMSHIELD™ Enhance Colours may increase the slipperiness depending on the surface and the quantities of sealer used.

CROMSHIELD™

Enhance Colours

Testing Approvals: N/A

Cleaning

- Equipment can be cleaned with lacquer thinners or CROMSHEILD™ Solvent.

Health & Safety

Safety Precautions

- Avoid breathing vapour. Wear organic vapour respirator meeting the requirements of AS1715 and AS1716.
- Provide good ventilation – open windows and doors and use circulating fans.
- Wear eye protection.
- Wear PVC or neoprene gloves. Avoid contact with skin.
- If product is splashed on skin it should be washed off with water before it can dry.
- Keep out of the reach of children.

First Aid

- Swallowed: If poisoning occurs contact a doctor or Poisons Information Centre. Do not induce vomiting. Risk of aspiration into lungs. Give water to drink.
- Eye: Gently flush with running water, holding eyelids open for 15 mins. Seek medical attention.
- Skin: Remove contaminated clothing and gently flush affected areas with soap and water. Seek medical attention if irritation develops. Launder clothing before re-use.
- Inhalation: Remove patient from exposure, into fresh air. Apply artificial respiration if patient has stopped breathing. Seek medical attention.

For detailed information refer to product label and the current Material Safety Data Sheet available from Crommelin. In the case of an emergency please call the Poisons Information Centre on 13 11 26

Transport and Storage

Sizes:	2L,	Flash Point:	43°C
Weights:	2Kg	UN Number:	1263
Dangerous Goods Class:	3.2	Poisons Schedule:	5
Hazchem Code:	3 (Y)		

Disclaimer

Crommelin and other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks. Any advice, recommendation, information, assistance or service provided by Crommelin in relation to its products or their use is given in good faith, however is provided without responsibility or liability. Customers are advised to undertake their own assessment to determine suitability of a product for the particular use intended. Due to the performance of any product being subject to a wide variety of field and surface conditions we are unable to assume liability for any loss, consequential or otherwise that may arise from the use of our products. Where a product is proven defective, our liability is limited to the replacement of the product.